

Study of non-cured MY-133: Refractive index vs. wavelength

The cured resin should be about 0.004 higher.

X	511.3	589.3	595.6	623.4	671	770	820	880	902.2
Y	1.33346	1.33147	1.33133	1.33078	1.32999	1.32876	1.32824	1.32768	1.32754

