

## Provisional DATA SHEET

### DC-150 : Dual Cure Low Modulus Optical Coating / Adhesive / Sealant

DC-150 is a Dual Cure low refractive index Coating/Adhesive/Sealant. It is cured by either UV radiation, heat, or both. The material can be used in situations where UV radiation is partially or fully blocked. It has excellent adhesion to glass, metals and some plastics. Its low modulus enables high endurance under repetitive, high amplitude thermal cycles.

#### Properties

	Liquid state
RI liquid at 589 nm	na
Density, g/cm <sup>3</sup>	1.06
Viscosity, cps @ 25°C	1800
	Cured state
RI cured at 589 nm	na
RI cured at 950 nm	1.478
Adhesion to glass, 90° Peel, g/cm	>1100
Elastic modulus, MPa	23
Tensile Strength, MPa	4
Elongation at Break, %	450
Hardness, Shore A	na
Volumetric Shrinkage, %	6

The product is supplied pre-filtered to below 1 micron particles.

#### Storage

1. Avoid unnecessary exposure to ambient light and moisture.
2. Long term storage should be in a cool place or in a refrigerator at 6-20°C.
3. The coating is supplied in glass bottles. Keep container closed to avoid moisture penetration.
4. The shelf life is 6 months.

#### Application

Curing can be achieved by any source of UV at 300-400nm. Typically, a dose of 1000-2000 mJ/cm<sup>2</sup> is necessary. To prevent tackiness on exposed surfaces, it is recommended to cure in an inert atmosphere (e.g. under nitrogen). There is no need for inert atmosphere when curing between two layers or in a mold (more on inert curing in the Technical Support page on our web site). If necessary a thermal curing can be activated by heating for 1-2 hours at 120°C. Keep the bottle closed in all times when not in use. The material is sensitive to light.

**Safety:** Refer to the SDS

Note: The above information is provisional. It is believed to be reliable, but it is not to be taken as a representation, warrantee or guarantee. Customers should perform their own QC, QA and evaluation tests.

Updated: February 25, 2019