

DATA SHEET

MY-150: Optical Coating / Adhesive

MY-150 is a low refractive index UV curable coating/recoating/adhesive. This is a low modulus flexible adhesive with excellent adhesion to glass, metals, ceramics and most plastics. It is characterized by a high plasticity, which minimizes any stress created by the shrinkage that accompanies UV polymerization.

Properties

	Liquid state
RI liquid at 589 nm	1.477
Density, g/cm ³	1.06
Viscosity, cps @ 25°C	2000
	Cured state
RI cured at 589 nm	1.496
RI cured at 950 nm	1.487
Adhesion to silica, 90° Peel, g/cm	>1100
Elastic modulus, MPa	5.5
Tensile Strength, MPa	2
Elongation at Break, %	340
Volumetric Shrinkage, %	6

The product is supplied pre-filtered to below 1 micron particles.

Storage

1. Avoid unnecessary exposure to ambient light and moisture.
2. Long term storage should be at ambient conditions of 10-30°C.
3. The coating is supplied in glass bottles. Keep container closed to avoid moisture penetration.
4. The shelf life is 12 months.

Application

Curing can be achieved by any source of UV at 300-400nm. Typically, a dose of 1000-2000 mJ/cm² is necessary. To prevent tackiness on exposed surfaces, it is recommended to cure in an inert atmosphere (e.g. under nitrogen). There is no need for inert atmosphere when curing between two layers or in a mold (more on inert curing in the Technical Support page on our website).

Keep the bottle closed in all times when not in use. The material is sensitive to light.

Safety: Refer to the SDS

Note: The above information is believed to be reliable, but it is not to be taken as a representation, warrantee or guarantee. Customers should perform their own QC, QA and evaluation tests.

Updated: May 18, 2025.