

DATA SHEET

RCT-155: Optical Coating

RCT-155 is a low modulus UV curable coating specially designed for recoating in a mold. The material was optimized for curing by both UV LED and UV Mercury lamps. A typical application is re-coating for optical fibers. The adhesion level was optimized for the ease of release from re-coating molds.

Properties

| | Liquid state |
|---|------------------|
| RI liquid at 589 nm | 1.533 |
| Density, g/cm ³ | 1.12 |
| Viscosity, cps @ 25°C | 3000 |
| Surface tension, dyne/cm | 20 |
| Color | Clear, yellowish |
| | Cured state |
| Transparency 450-1600 nm, 300 micron film | 99% |
| RI cured at 589 nm | 1.550 |
| RI cured at 1550 nm | 1.540 |
| Adhesion to silica, 90° Peel, g/cm | 80 |
| Secant Modulus @2.5% | 34 |
| Young Modulus, MPa | 52 |
| Tensile Strength, MPa | 7 |
| Elongation at Break | 100 |

The product is supplied pre-filtered to below 1 micron particles.

Storage

- 1. Avoid unnecessary exposure to ambient light and moisture.
- 2. Long term storage should be at ambient conditions of 15-30°C. Do not refrigerate. The material may show haze below 10°C. It will clear up upon warming back to ambient conditions.
- 3. The shelf life is 12 months.

Application

Curing can be achieved by any source of UV at 300-400nm. Typically, a dose of 1000-2000 mJ/cm2 is necessary. Keep the bottle closed in all times when not in use. The material is sensitive to light.

Safety: Refer to the SDS

Note: The above information is believed to be reliable, but it is not to be taken as a representation, warrantee or guarantee. Customers should perform their own QC, QA and evaluation tests.

Updated: May 20, 2025